



* Trademark of SABIC Innovative Plastics IP BV

INSULATION VALUES







K,U = OVERALL HEAT TRANSFER COEFFICIENT
R = OVERALL THERMAL RESISTANCE CONVERSION

K-VALUE [W/m² °C] x 0.17611 = U-FACTOR [BTU/h ft² °F]

$$U \times 5.68 = K \qquad R = \frac{1}{U} \qquad U = \frac{1}{R}$$

The unit conversion from W/m² °C to BTU/h ft² F is 1 W/m² °C is equal to 0.17611 BTU/h ft² °F or 1/5.678269 BTU/h ft² °F

EXAMPLES:

product		<u>K-VALUE</u> W/m ² °C	<u>U-FACTOR</u> BTU/h ft ² °F	<u>R</u> h ft ² °F/BTU
16mm		2.27	0.40	2.50
16mm		1.84	0.324	3.09
25mm		1.45	0.255	3.92
35mm		1.187	0.209	4.78
50mm		0.982	0.173	5.78
Thermoclick 40mm		1.412	0.248	4.02

Please call us with any technical question you have. We'll do our best to get you an answer

tech.service@ameriluxinternational.com

www.daylightspec.com

1212 Enterprise Drive, De Pere, Wisconsin 54115
 Telephone: 920.336.9300 Fax: 920.336.9301