



SGS U.S. Testing Company Inc.

291 Fairfield Avenue • Fairfield, NJ 07004 • Tel: 973-575-5252 • Fax: 973-575-8271

CLIENT: GE Plastics
One Plastics Avenue
Pittsfield, Massachusetts 01201

Test Report No: 160999-39	Date: May 23, 2002
----------------------------------	---------------------------

The following sample was submitted by the Client as:

Lexan Thermoclear Sheet

DATE OF RECEIPT: April 3, 2002, May 7, 2002 and May 14, 2002

TESTING PERIOD: April 24, 2002 to May 22, 2002

AUTHORIZATION: Client's Purchase Order Number P18093000.

TESTS REQUESTED: The submitted sample was tested in accordance with the procedures outlined in ASTM D1929-96, "Standard Method of Test for Ignition Properties of Plastics". A specimen weight of 3 grams was maintained for the tests.

PREPARED BY:

Nick Kitov, Technician
Products Evaluation

**SIGNED FOR AND ON BEHALF OF
SGS U.S. TESTING COMPANY INC.**

Piyush Shah, Manager
Products Evaluation

iv

Page 1 of 2

This report is issued by SGS U.S. Testing Company Inc. under its General Conditions for Testing Services, as printed on reverse side. SGS U.S. Testing's responsibility under this report is limited to proven negligence and will in no case be more than the amount of the testing fees. Except by special arrangement, samples are not retained by SGS U.S. Testing for more than 30 days. The results shown on this test report refer only to the sample(s) tested unless otherwise stated, under the conditions agreed upon. Anyone relying on this report should understand all of the details of the engagement. Neither the name, seals, marks nor insignia of SGS U.S. Testing may be used in any advertising or promotional materials without the prior written approval of SGS U.S. Testing. The test report cannot be reproduced, except in full, without prior written permission of SGS U.S. Testing Company Inc.

Member of the SGS Group (Société Générale de Surveillance)



SGS U.S. Testing Company Inc.

Report No.:

166999-39

DATE: May 23, 2002

PAGE 2 OF 2

CLIENT: GE Plastics

TEST RESULTS:

<u>Sample</u>	<u>Flash Ignition Temperature, °F</u>	<u>Flash Ignition Temperature, °C</u>	<u>Self-Ignition Temperature, °F</u>	<u>Self-Ignition Temperature, °C</u>
Lexan Thermo- clear Sheet	940	504.4	1110	598.9

Visual Observations: Combustion for flash and self-ignition was flaming.**Behavior of Specimen:** Melting, smoking, charring.

These test results relate only to the behavior of test specimens under the particular conditions of the test. They are not intended to be used, and shall not be used, to assess the potential fire hazards of a material in use.

End of Report